

Aluminium alloy specification

Components	Impurities	Percentage (%)
Silicon		0.05 - 0.20
Zinc		3.50 - 5.00
Titanium		0.01 - 0.05
Bismuth		0.05 - 0.15
Indium		0.02 - 0.05
Aluminium	Remainder	
	Copper	0.01 max
	Iron	0.15 max
	Others each	0.02 max
	Others total	0.05 max



Electrochemical capacity: 2700 Ahr / Kg nominal

Solution potential: -1100 mV vs. Ag / AgCl reference cell nominal (in seawater)

Other specifications are available on request.

Note: All dimensions and weights are nominal. Dimensions in mm
All data is subject to change without prior notice
Anode can also be provided backside coated

Nett Weight: 1.7 Kg
Gross Weight: 2.2 Kg

Date:			Cathodic Protection Division Rietdekkerstraat 16 P.O. Box 4222 2980 GE Roldenkerk Netherlands Tel: +31 (0)180 48 28 28 E-mail: sales@mme.nl www.mme-group.com		Projection:  Scale: 1:3.75
			Order number:		
Rev. Description:	Drawn: PdG	Date: 31-07-13	Project:		Sheet 1/1
	Checked: JdR	Date: 31-07-13	Dwg: MME 17A		
Rev. Description:	Approved: PM	Date: 31-07-13	Copyright MME. No part of this drawing may be copied, disclosed, or made public, in any form, without prior written consent of Materiaal Medingen Europe.		